

# SUPERFAST ALUMINIUM

## Product Description

Superfast Aluminium Epoxy Putty Stick is a fast-setting, industrial-strength polymer compound that enables permanent repairs to anything made of aluminium. It also bonds to other metals wood, glass, masonry, and many plastics.



Each handy stick contains pre-measured portions of activator and base throughout – no measuring or mixing tools are necessary. As the epoxy is mixed, the two contrasting colours blend into one colour to indicate complete mixing. The consistency eliminates drips and runs, facilitates adhesion to the substrate, and allows the material to be shaped and formed as needed before curing begins. Superfast Aluminium cures to a light grey metallic colour. Once cured, it can be tapped, drilled, screwed, sawed, machined, ground, filed, or painted. It is non-rusting and will not corrode.

Suitable for interior or exterior use, it is resistant to water, chemicals, and temperature extremes. Superfast Aluminium contains no solvents or VOC's. It's non-flammable and releases no noxious fumes. It won't shrink or pull away. The unused portion stays fresh for future use when saved in its original package.

Superfast Aluminium has a work life of approximately 4-7 minutes. Within 5-10 minutes it will harden and form a cohesive bond. After 1 hour, the system can be put back into service.

Superfast Aluminium has a work life of approximately 4-7 minutes. Within 5-10 minutes it will harden and form a cohesive bond. After 1 hour, the system can be put back into service.

## Performance Data\*

MINIMUM SHELF LIFE (months @ 24°C.)	24
HARDNESS, SHORE D (full cure, 24 hrs.)	65
LAP SHEAR TENSILE STRENGTH (MPa)	
On Aluminium	3.4
On Steel	4.1
COMPRESSIVE STRENGTH (MPa)	83
DENSITY (gm/cm <sup>3</sup> , lb/gal)	1.6, 13.4
SHRINKAGE (%)	<1
NON-VOLATILE CONTENT (%)	100
ELECTRICAL RESISTANCE (megohms)	30,000
DIELECTRIC STRENGTH (volts/mil)	300
UPPER TEMPERATURE LIMIT	
Continuous (°C)	120
Intermittent (°C)	150

### CHEMICAL RESISTANCE

Resistant to hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions and dilute acids and bases.

\*Typical properties: for information only; not for specification purposes.